



# **VICOFIL**

Tile grout

# **Properties- Applications**

**VICOFIL** is a high strength - water-repellent tile grout based on cement and acrylic resins. It is suitable for grouting all types of ceramic wall and floor tiles, slabs of natural stone (granite, marble) indoors and outdoors. **VICOFIL** gives a smooth surface finish, suitable for joint width from 2 to 10 mm and is available in 24 different colorings.

#### How to use

Grouting is performed preferably by means of special plastic crosses of 2 - 10 mm width. Joints should be thoroughly cleaned and soaked. In **VICOFIL** is added 30% water by weight, followed by thorough mixing with a low speed drill and after maturing or mixture - into 10 minutes time- stirring is repeated. Joints are filled with rubber spatula, followed by first cleaning with a slightly damp sponge and after the complete drying of the joints becomes final cleaning preferably with a dry cloth.

#### Technical characteristics

Grout Type	CG2 WA (EN 13888)		
Base	Cementitious mortar		
Colorings	24 standard		
Water demand	1,5 l/bag 5 kg		
Bulk density of dry mortar	1,5 ± 0,30 kg/l		
Bulk density of fresh mortar	2,00 ± 0,50 kg/l		
Application temperature	Από +5 <sup>0</sup> C έως +35 <sup>0</sup> C		
Abrasion resistance	≤ 1000 mm <sup>3</sup>		
Compressive strength after:			
28 days	39,00 N/mm <sup>2</sup>		
25 freeze-thaw cycles	39,00 N/mm <sup>2</sup>		
Flexural strength after:			
28 days	7,7 N/mm <sup>2</sup>		
25 freeze-thaw cycles	7,7 N/mm <sup>2</sup>		
Shrinkage setting	≤ 2 mm/m		
Water absorption after:			
30 min	≤ 2 g		
240 min			
Pot Life	At least 4h at +20°C		
Foot traffic	After 12h at +20°C		



## **VICOFIL**

## Consumption

Tile dimensions in	Joint thickness			
mm	3 mm	5 mm	10 mm	
200 x 200 x 7	390	640	1280	
300 x 300 x 8	300	490	980	
400 x 400 x 8	230	370	740	
500 x 500 x 8	180	300	600	
400 x 400 x 10	280	460	920	

# Packaging - Colorings

**VICOFIL** is available in 5 kg plastic bags in cardboard boxes and in colorings as following:

01	White	42 Ruby	78	Basalt grey
06	White mint	51 Jacinth	79	Slate grey
13	Narcissus	52 Blue azure	81	Caramel
21	Anemone	61 Pistachio	82	Cotto
22	Bahama beige	62 Green pale	83	Red brown
23	Jura Beige	71 Manhattan grey	84	Maroon
31	Magnolia	73 Topaz grey	85	Tabac
41	Violet	75 Sand grey	86	Brown

## Storage

24 months from date of production provided that they kept in a dry environment and temperatures above zero.

## Hygiene Measures

**VICOFIL** contains cement and thus reacts alkaline with water and is considered irritating.



#### VIMATEC - N. VIDALIS S.A.

CONSTRUCTION CHEMICALS TECHNOLOGIES **Head:** 1-3, Makedonias str, GR-546 41 Thessaloniki GREECE
Tel: +30-2310 858561, +30-2310 843093 Fax: +30-2310843566
e-mail:info@vimatec.eu